



# Lider

CONTA İMALATI & İNŞ. MALZ.  
SANAYİ & TİCARET LTD. ŞTİ.



RAPOR NO:	0007
TEST TARİHİ:	06.10.2012
PARTİ NO:	0210120006

PROJE BİLGİLERİ	
TEST STANDARDI:	TS EN 681-1 ISO 815
TEST TANIMI:	DÜŞÜK SICAKLIKLARDA BASINÇ ALTINDA KALICI EZİLME ORANININ TAYİNİ

NUMUNE: VULKANİZE KAUÇUK SİLİNDİR (SBR)

DENEY PARÇASI: TİP A -1 ADET

SERTLİK: 55

YAĞLAYICI : KULLANILMADI

LABORATUVAR SICAKLIĞI: 23°C

KONDİSYONLAMA: 3 SAAT

DENEY SICAKLIĞI: -10°C

DENEY SÜRESİ: 72 SAAT

DENEY PARÇASI h°: 12 mm.

DENEY PARÇASI h1: 11,75 mm.

MESAFE AYARLAYICI: 8.25 mm

SONUÇ: -10°C DERECE 72 SAAT BEKLETİLEN TİP A DENEY PARÇASI %14,60 EZİLMİŞTİR.